

SUBSTITUTE SPECIFICATION, CLEAN VERSION

SUMMARY

In accordance with the present invention, methods and a composition are provided for producing an optical composite with the optical clarity and scratch-resistance of a glass and the tensile strength of a polymer. In addition, the present invention also provides an optical composite with the optical clarity of a glass, yet protected by the tensile strength of a polymer.

The present invention includes a glass and polymer composite composed of a glass having a shape, a center, a margin; the plastic has a center, a shape adapted to receive the shape of the glass, and a margin; a sealant is disposed between the margin of the glass and the margin of the plastic, whereby the central portions of the glass and the plastic are devoid of the sealant.

The present invention includes having the glass contain metallic compounds selected from the group consisting of silver salts, copper salts gold, palladium, cadmium chalcogenides, noble metal colloids, and ferrites.

The present invention also includes a method of annealing plastic by heating the plastic indirectly using microwave radiation while the plastic rests on a rigid, microwave-absorbing glass surface.

The present invention also includes a method of forming a glass and plastic composite using optical contacting to hold the glass and plastic portions together using microwave radiation.

The present invention also includes a method of enhancing the kinetic reaction strength of

a sealant using microwave radiation.

The present invention also includes having the glass be photochromic.

The present invention also includes having the plastic, in whole or in part, be selected from the group consisting of polycarbonate, polyurethane, polystyrene, fluorocarbon and polymethylmethacrylate.

The present invention also includes having the sealant be selected from the group consisting of silicones, shellac and lacquer, silane coupling agents, disilyl crosslinker compounds, epoxy resins, crosslinkable polyethylene vinylacetate terpolymer, polyvinyl butyral and polysulfide.

The present invention also includes having the glass and plastic be transparent and refractive.

The present invention also includes having the margin of the glass having at least one appendage and the margin of the plastic defining an aperture shaped for receiving the appendage of the glass.

The present invention also includes having the margin of the plastic having at least one appendage and the margin of the plastic defining an aperture shaped for receiving the appendage of the plastic.

The present invention also includes having the percentage of glass in the composite be between about 0.01 to 99.99 %.

The present invention also includes having a microwave-transparent spring-loaded vice

adapted to hold together the glass and the plastic.

The present invention also includes having a vice whose spring tension is between about 0.01 to 200 foot pounds.

The present invention also includes having a weighted microwave-transparent, vice adapted to hold together the glass and the plastic.

The present invention also includes having a vice whose holding weight is between about 0.01 to 100 pounds.

The present invention also includes a method of forming a glass and plastic composite by forming a glass having a margin and a center to a particular shape; then forming a plastic having a margin and a center to a shape essentially adapted to receive the shape of the glass; then applying sealant only to the margin of the glass and the margin of the plastic, whereby the center of the glass and the center of the plastic are devoid of the sealant; then placing together the glass and the plastic; then placing the glass and plastic into a vacuum chamber; then applying vacuum pressure to the glass and the plastic; then placing the vacuum chamber into a microwave oven; and then finally, applying microwave radiation to the glass and the plastic for an effective time.

The present invention also includes a method of forming a glass and plastic composite using an applied vacuum pressure of between about 0.01 to 200 torr.

The present invention also includes a method of forming a glass and plastic composite using microwave radiation applied at between about 10 watts to 100,000 watts and a frequency of between about 3Ghz to 3000Ghz.

The present invention also includes a method of forming a glass and plastic composite using microwave radiation that is applied for between about 0.01 to 100 minutes.

The present invention also includes a method of forming a glass and plastic composite by forming a glass having a center and a margin to a particular shape; then forming a plastic having a margin and a center to a shape essentially adapted to receive the shape of the glass; then applying sealant only to the margin of the glass and the margin of the plastic, whereby the center of the glass and the center of the plastic are devoid of the sealant; then applying force to the glass and plastic by placing the glass and plastic into a microwave-transparent vice adapted to hold together a glass and plastic composite using microwave radiation that is applied for between about 0.01 to 100 minutes.

The present invention also includes a method of forming a glass and plastic composite using microwave radiation wherein the microwave radiation is applied at between about 10 to 100,000 watts and at a frequency of between about 3Ghz to 3000Ghz..

The present invention also includes a method of forming a glass and plastic composite using microwave radiation where sealant is applied to the glass and the plastic before the glass and the plastic are placed together and an effective amount of distilled water is applied to the center of the glass and the center of the plastic before applying the microwave radiation.

The present invention also includes a method of forming a glass and plastic composite, where sealant is applied to the glass and the plastic before the glass and the plastic are placed together, that uses gravity to hold the glass and the plastic together.

The present invention also includes a method of forming a glass and plastic composite, where sealant is applied to the glass and the plastic before the glass and the plastic are placed together, that uses spring tension to hold the glass and the plastic together. .

The present invention also includes a method of forming a glass and plastic composite by forming a glass having a center and a margin to particular shape; then forming a plastic having a margin and a center to a shape essentially adapted to receive the shape of the glass; then applying force to the glass and plastic by placing the glass and plastic into a microwave-transparent vice adapted to hold together the shape of the glass and the shape of the plastic; then placing the glass and plastic into a vacuum chamber; then applying vacuum pressure to the glass and the plastic; then placing the vacuum chamber into a microwave oven; then applying microwave radiation to the glass and the plastic; then applying sealant only to the margin of the glass and the margin of the plastic, whereby the center of the glass and the center of the plastic are devoid of the sealant; and finally, applying microwave radiation to the glass and the plastic for an effective time.

The present invention also includes a method of forming a glass and plastic composite, that uses gravity to hold the glass and the plastic together, where sealant is applied to the glass and the plastic after the glass and the plastic are placed together and before applying microwave radiation to the glass and the plastic.

The present invention also includes a method of forming a glass and plastic composite, that uses spring tension to hold the glass and the plastic together, where sealant is applied to the glass and the plastic after the glass and the plastic are placed together and before applying

microwave radiation to the glass and the plastic.

The present invention also includes a method of forming a glass and plastic composite using microwave radiation where sealant is applied to the glass and the plastic after the glass and the plastic are placed together and an effective amount of distilled water is applied to the center of the glass and the center of the plastic before applying the microwave radiation.

The present invention also includes a method of forming a glass and plastic composite, where sealant is applied to the glass and the plastic after the glass and the plastic are placed together and before applying microwave radiation to the glass and the plastic, where vacuum pressure is applied for between about 0.01 to 200 torr.

The present invention also includes a method of forming a glass and plastic composite, where sealant is applied to the glass and the plastic after the glass and the plastic are placed together and before applying microwave radiation to the glass and the plastic, where the microwave radiation is applied for between about 0.01 to 100 minutes.

The present invention also includes a method of forming a glass and plastic composite, where sealant is applied to the glass and the plastic after the glass and the plastic are placed together and before applying microwave radiation to the glass and the plastic, where the microwave radiation is applied for between about 10 to 100,000 watts and a frequency of between about 3Ghz to 3000Ghz..

The present invention also includes a method of forming a glass and plastic composite, where sealant is applied to the glass and the plastic after the glass and the plastic are placed

together and before applying microwave radiation to the glass and the plastic, where the microwave radiation is applied for between about 0.01 minutes to 100 minutes.

The present invention also includes a glass and plastic composite formed by joining a glass having a margin and a center and a particular shape to a plastic having a margin and a center to a shape essentially adapted to receive the shape of the glass; then applying sealant only to the margin of the glass and the margin of the plastic, whereby the center of the glass and the center of the plastic are devoid of the sealant; then placing together the glass and the plastic; then placing the glass and plastic into a vacuum chamber; then applying vacuum pressure to the glass and the plastic; then placing the vacuum chamber into a microwave oven; and then finally, applying microwave radiation to the glass and the plastic for an effective time.

It is a characteristic of the present invention to provide a method of bonding together glass and plastic, while maintaining their original optical clarity.

It is a characteristic of the present invention to provide method to prevent plastic from becoming scratched by protecting it with a layer of glass.

It is a characteristic of the present invention to provide a method to prevent glass from becoming damaged by protecting it with a layer of plastic.

It is a characteristic of the present invention to provide a method to provide glass-like optical characteristics to plastic by bonding the plastic to a rigid glass surface.

It is a characteristic of the present invention to provide method of making a glass and plastic composite that is photochromic and capable of being performed by optical labs of diverse

size.

It is a characteristic of the present invention to provide a method of differentially heating the glass and the plastic during the bonding process of forming the resultant optical composite.

It is a characteristic of the present invention to provide a method of optically contacting together the glass and the plastic during the bonding process of forming the resultant optical composite using microwave radiation.

DETAILED DESCRIPTION OF THE INVENTION

The description of the present invention is organized as follows: a general description, including a description of operation of one embodiment is described, then alternative embodiments are described.

The optical composite is composed of at least one piece of glass and one piece of plastic. The glass is a microwave absorbent glass. The plastic is heated indirectly by heat transmitted to it by the adjacent microwave-heated the glass portion. The glass and plastic's margins are then sealed together with a sealant.

Optical contacting means to adhere two surfaces together through molecular attraction without the use of an adhesive.

Optically correcting means to correct optical imperfections.

Anneal means to use heat to relieve a plastic's internal stresses.

Plastic means the physical characteristic of being able to be shaped, molded, or modeled such that the resulting change of shape is permanent.

Glass means an amorphous, vitreous substance that has a disordered molecular arrangement, but is mechanically rigid and capable of transmitting light.

The glass can include silver salts, copper salts gold, palladium, cadmium chalcogenides, noble metal colloids, and ferrites.

The plastic can include, in whole or in part, polycarbonates, polyurethanes, polystyrenes, fluorocarbons and polymethylmethacrylates.

The sealant can include, in whole or in part, silicones, shellac, lacquer, epoxy, silane coupling agents, disilyl crosslinker compounds, epoxy resins, crosslinkable polyethylene vinylacetate terpolymer, polyvinyl butyral, polysulfide, and commercially available, crosslinkable polyethylene vinylacetate terpolymer.

The most preferred silane coupling agents are those which are commercially available and which are recognized by those skilled in the art as being effective coupling agents. In particular, silane coupling agents include N-(2-aminoethyl)-3-aminopropyltrimethoxysilane, 3[2(vinylbenzylamino) ethylamino]propyltrimethoxysilane, 3-methacryloxypropyltrimethoxysilane, 3- glycidoxypropyltrimethoxysilane, triacetoxylvinylsilane, tris-(2-methoxyethoxy) vinylsilane, 3-chloropropyltrimethoxysilane, 3-aminopropyltrimethoxysilane, vinyltrimethoxysilane, mercaptopropyltrimethoxysilane, mercaptopropyltriethoxysilane and the azide functional silanes of

the formula $X_3SiR''SO_2N_3$, where X denotes a hydrolyzable group such as an alkoxy, an alkylalkoxy or a chloro radical, and R'' denotes a divalent organic radical.

The syntheses of the disilyl crosslinker compounds are known in the art. The disilylalkyl compounds can be synthesized by reacting chloroalkyltrialkoxysilane with tetraalkoxysilane (represented by the formula SiX_4 where X is an alkoxy group) in the presence of lithium. The bis(trimethoxysilyl)benzene compounds can be synthesized by reducing bis(trichlorosilyl)benzene with lithium aluminum halide followed by methanolysis as described in Preparation and Characterization of Disilylbenzene and Bis(trimethoxysilyl)benzene, Bilow, et al., J. Org. Chem. 26(3) 929, 1961. The disilyl crosslinker can also be synthesized by any of the means taught in U.S. Pat. No. 3,179,612, especially, by the method taught in Example 2 of said patent. The disilyl crosslinker compounds can also be synthesized by reacting polyamines with chloroalkylsilanes according to the method taught in U.S. Pat. No. 4,448,694.

In a preferred embodiment, the glass contains silver salts, copper salts, gold, palladium, cadmium chalcogenides, noble metal colloids, and ferrites. The glass and the plastic are placed in a vacuum while microwave radiation is applied to the resulting optical composite. After removal from the microwave radiation, and while still held in a microwave-transparent vice, a sealant is applied to the margins of the glass and the plastic at their junction. The glass and plastic may each be refractive. The glass percentage of the composite is between about 0.01% to 99.99%. The plastic percentage of the composite is between about 0.01% to 99.99%. The glass and plastic each range from being opaque to being transparent.

The vice can include conventional glasses, conventional plastics, and conventional natural and synthetic rubbers.

The microwave-transparent materials can include conventional glasses, conventional plastics, and conventional natural and synthetic rubbers.

Photochromic means a visible and reversible change in light transmission or color that is induced by exposure of the material to electromagnetic radiation.

Refractive means that the material is capable of bending a particular wavelength of light.

Opaque means not transmitting a particular wavelength of light.

Transparent means transmitting at least 99.99% of a particular wavelength of light.

Microwave-transparent means that not absorbing microwave radiation.

In another preferred embodiment, distilled water is placed between the glass and the plastic before microwave radiation is applied.

In another preferred embodiment, the optic fiber is made up of 3 to 4 parts: a central core made of silicon dioxide glass, though other glasses may also be used, for transmitting the optical signals; surrounding the core is a cladding; a buffer coating in turn surrounds the cladding; and an optional final coat, the sheath surrounds the buffer.

Cladding means a thin layer of glass, plastic, or polymer coating with an index of refraction lower than the core, surrounding the core. The function of the cladding is to reflect light back into the core as it moves down the fiber. The cladding may be multi-layered. These cladding layers may be of different indices of refraction. Claddings are usually silica, but other

glasses, silicone, and other polymers may be used; however, the refractive index must be lower than the core to allow light to propagate through the fiber.

The buffer coating is a plastic or a polymer that protects the core and cladding from moisture, scratches, and other contamination while imparting additional strength to the fiber.

The sheath is an optional final coating made of metal, plastic or a polymer and provides additional strength, stiffness, protection and resistance to moisture.

In one preferred embodiment, the core is made of glass and polymer cladding is bonded on to the optic fiber using heat generated from microwave radiation absorbed by the optic fiber.

In another preferred embodiment, the core is made of glass and the polymer cladding is optically contacted on to the optic fiber using heat generated from microwave radiation.

In another preferred embodiment, the core is made of glass and a polymer sheath is bonded on to the optic fiber using heat generated from microwave radiation absorbed by the optic fiber.

In another preferred embodiment, the core is made of glass and a buffer coating is bonded on to the optic fiber using heat generated from microwave radiation absorbed by the optic fiber.

While a few presently preferred embodiments of the invention are shown and described, it will be apparent to those skilled in the art that various changes and modifications, such as substituting ultraviolet radiation and ultraviolet absorbing compounds for the present invention's microwave radiation and microwave absorbing compounds, may be made therein without departing from the spirit of the invention or from the scope of the appended claims.